




Expose Bricks

Traditional Bricks

Terracotta Red

Code
BT-1



Specifications

Length	Width	Height	Weight	Strength
220 mm	100 mm	67 mm	2.5 Kg	Above 75kg/cm ²

Water Absorption
< 15%

Coverage per sq.ft. (10mm joint)
4" Wall (5.5 Nos bricks)
9" Wall (11 Nos bricks)



www.jbcbricks.com

“God created Human from clay” and “Human created wonderful bricks from clay” The wonderful creation out of clay by human. The manual hand made traditional bricks. We manufacture Teraacotta red Brick. The traditional method brings out unique bricks with beautiful texture and color as the shaping process involves throwing the clot of clay in a mold box flushed with fine sand, every clot of clay that strikes the mold does so in a slightly different way which leads to a different texture for every brick. The particle of sand leads to many different textures, the difference of humidity in the clay clots leads to different textures, a dynamic combination of all this leads to a product that is random, beautiful yet amazingly strong, crisp in shape and can be used to create structures for generations to come.

Features

- Acoustic Insulation
- Durabilty
- Vintage Look
- Environment Friendly
- Fire Resistance
- High Strength

